

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 01-234339

(43)Date of publication of application : 19.09.1989

---

(51)Int.Cl.

C03B 19/00

C04B 41/86

H01L 23/10

---

(21)Application number : 63-057549

(71)Applicant : MURATA MFG CO LTD

(22)Date of filing : 11.03.1988

(72)Inventor : TAKAOKA KEN

YONEDA YASUNOBU

NAGAI AKIRA

---

### (54) FORMATION OF GLASS FILM

#### (57)Abstract:

PURPOSE: To form the title glass film useful for IC package sealing, etc., free of pinholes, and having excellent airtightness by applying and printing a glass paste consisting of low-melting-point glass powder, a sublimable binder, and a solvent on a body to be coated, degreasing the material in an inert atmosphere, then heating, and melting the material.

CONSTITUTION: A vehicle consisting of PbO-B<sub>2</sub>O<sub>3</sub> based low-melting-point glass powder having about 400°C softening point, a low-temp. sublimable binder [e.g., 'Dianal (R)' made by the Mitsubishi rayon], and a solvent such as butylcarbitol acetate is mixed with glass powder in 9/1 weight ratio of the powder to vehicle to obtain a glass paste. The paste is then applied or serially screen-printed four to five times on a body to be coated (e.g., the sealing surface of a package substrate made of alumina). The material is heated at a temp. up to the softening temp. of the glass powder in an inert atmosphere, and degreased. The material is then heated at a temp. higher than the softening temp. to melt the glass powder, and then cooled to form a glass film on the body to be coated.